

Density calcium silicate boards (annealed)

CALCAST® CC 500

CALCAST® CC 500 is a ceramical insulation material based on calcium silicate with a bulk density of 1,200 kg/m³.

The temperature limit for application is 1,200 $^{\circ}\text{C}$. The limit is 200 $^{\circ}\text{C}$ higher in comparison to the other **CALCAST** $^{\circ}$ grades.

CALCAST® CC 500 has a high thermal shock resistance and alternating thermal stress load. This is generated by the low shrinkage of the material at elevated temperatures.

The material is not wetted by liquid aluminium. Ideal is the use as cover for launders during preheating and transport of metal. Further areas of application are e. g. the insulation of furnace lids, walls of continuous furnaces etc.

Machining

CALCAST® CC 500 can be precisely machined to close tolerances. With our 5-axis processing machines we can produce the most complicated geometrics.

SPECIAL FEATURES

- thermal fatigue resitance
- temperature limit of 1200 °C
- dimensionally stable
- no wetting with liquid non-ferrous metals
- machinable in close tolerances



CALCAST® CC 500

| CALCAST® CC 500 | | Method | Unit | | |
|---|--|-------------|------------------------------------|--|-----|
| Upper application limit temperature | | EN 1094-6 | °C | 1,200 | |
| Bulk density (± 10 %) | | EN 1602 | kg/m³ | 1,200 | |
| Open porosity (in acc. with standard) | | EN 993-1 | % | 60 | |
| Compression strength | | EN 826 | MPa | 11 | |
| Flexural strength | | EN 12089 | MPa | 7 | |
| Hardness | | DIN 53505 | Shore D | 50 | |
| Shrinkage after 12 h | | EN 1094-6 | | | |
| Length and width | 750 °C | | % | 0.05 | |
| Thickness | 750 °C | | | 0.40 0.10 | |
| Length and width | 1,000 °C | | | | |
| Thickness | 1,000 °C | | | 0.70 | |
| Thermal conductivity λ at t _m | 200 °C | EN 12667 | W/(m K) | 0.22 | |
| " | 400 °C | | | 0.24 | |
| | 600 °C | | | 0.26 | |
| | 800 °C | | | 0.30 | |
| Specific thermal capacity | | | kJ/(kg K) | 0.8-1.2 | |
| Coefficient of expansion | RT-750 °C | DIN 51045-5 | | T | // |
| | | | | | |
| // parallel to board plane | | | K ⁻¹ x 10 ⁻⁶ | 3.7 | 5.9 |
| Chemical composition | | | | | |
| Calcium silicate | | | % | 96-97 | |
| (CaO-; MgO-; Al ₂ O ₃ -) silicate | | | | - | |
| R _v O _v (R=Fe, Ti, K, Na) | | | | 0.5 | |
| Annealing loss | | | % | 3 | |
| Dimensions | | | | | |
| Standard sizes | | Tolerances | | | |
| | Length | ±2; *0/+50 | mm | 1,000/1,500/3,000* | |
| | Width | 0/+20 | mm | 1,250 | |
| | Thickness | 0/+0.8 | mm | 12.7/19.1/25.4/31.8/38.1/50.8/76.2/101.6 | |
| | Surfaces ground on both sides, without trimming. | | | | |
| Other dimensions are available on request. | | | | - | |

The properties mentioned are typical values obtained according to the listed methods. Product variations have to be taken into account. The data do not represent guaranteed properties and cannot be used for any warranty claim. Data are subject to technical modifications.

