

## SILCAFLEX LS 126 LOOSE WOOL

**SILCAFLEX LS 126 loose wool** is made of lubricated, long-fiber aluminum silicate fibers designed for the highest performance requirements.

SILCAFLEX	Unit	LS 126 loose wool
Classification temperature	°C	1,260
Upper application limit temperature		1,150
Mean Fiber Diameter	µm	2.0 - 3.5
Shot contents	%	< 42
Chemical composition		
SiO <sub>2</sub>	%	53 - 55
Al <sub>2</sub> O <sub>3</sub>		44 - 46
Other		< 1

The properties mentioned are typical values obtained according to the listed methods. Product variations have to be taken into account. The data do not represent guaranteed properties and cannot be used for any warranty claim. Data are subject to technical modifications.

